

ROSCO-BPR

Introduction:

ROSCO-BPR is bitumen based primer which contains volatile inflammable solvent. It is a thin black liquid applied with a brush over a cleaned, dry concrete surface to act as a primer, increasing the bonding property between concrete and mastic membrane.

Surface Preparation:

Steel surface should be free from rust, scale, grease, oil, etc. Preparation can be done by wire brushing and sand blasting or by chemical etching.

Concrete surface must be cleaned of all lubricants, previous coatings, etc. If the surface is contaminated by acid, it must be neutralized, washed with fresh water, and allowed to become absolutely dry prior to application.

Properties :

Drying time	: Not more than Eight (8) hours .
Consistency	: Smooth & uniform suitable for application by brush
Finish	: Smooth semi- glossy .
Colour	: Black .
Flash point	: 30 ° C minimum .
Self life	: 12 month at Room temperature (under shade)
Dry film thickness	: 30 -35 Micron / coat .
Coverage	: 3 to 4m ² per ltr. per coat.

Now :- Salt – Acid – Alkalies –Solvents –Corrosion –Temp.-Dirt:- (No Entry)

For, R.C. Corrocare Industries Pvt Ltd

Mobile No :- +91-9725-2559-59 / +91-9737-5659-45 Email ID : rahul@floorsandcoatings.com / info@floorsandcoatings.com